

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup>:</b> <b>C04B 14/00, 14/10, 33/02, C09C 1/42</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 97/30950</b> <b>(43) International Publication Date:</b> 28 August 1997 (28.08.97)
<b>(21) International Application Number:</b> PCT/US97/02706 <b>(22) International Filing Date:</b> 21 February 1997 (21.02.97)  <b>(30) Priority Data:</b> 60/012,143                      23 February 1996 (23.02.96)                      US  <b>(71) Applicants:</b> SOUTHERN CLAY PRODUCTS, INC. [US/US]; 1212 Church Street, Gonzales, TX 78629 (US). THE DOW CHEMICAL COMPANY [US/US]; 1790 Building, P.O. Box 1967, Midland, MI 48641-1967 (US).  <b>(72) Inventors:</b> GONZALES, Antonio; P.O. Box 395, Moulton, TX 77975 (US). NICHOLS, Kevin, L.; 305 Rosemary Lane, Lake Jackson, TX 77566 (US). POWELL, Clois, E.; 336 Lake Ridge Drive, Seguin, TX 78155 (US).  <b>(74) Agent:</b> RENDA, Barbara, L.; Klauber & Jackson, 411 Hack- ensack Avenue, Hackensack, NJ 07601 (US).		<b>(81) Designated States:</b> AL, AU, BA, BB, BG, BR, CA, CN, CU, CZ, EE, GE, HU, IL, IS, JP, KP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, TR, TT, UA, UZ, VN, YU, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> IMPROVED ORGANOCCLAY COMPOSITIONS  <b>(57) Abstract</b>  Organoclay compositions which comprise the reaction product of a smectite-type clay having an ion exchange capacity of at least 50 meq. wt. per 100 g. clay (active basis), and mixture of a quaternary ammonium compound and a chain transfer agent which is a thiol, $\alpha$ -methylketone, $\alpha$ -methylalcohol or a halogen compound are useful agents for use in the processes for the preparation of thermoplastic materials.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

## IMPROVED ORGANOCCLAY COMPOSITIONS

BACKGROUND OF THE INVENTION

5 This invention relates generally to organoclays, and, more specifically, to improved organoclays which are produced by the reaction of the organoclay with an chain transfer agent.

Organoclays, representing the reaction product of a smectite-type clay with a quaternary ammonium compound, have long been known for use in gelling of  
10 organic liquids such as lubricating oils, linseed oil, toluene and the like. A large variety of highly useful products, such as lubricating greases, are producible through use of such gelling agents. The procedures and chemical reactions pursuant to which these organoclays are prepared, are well-known. Thus, under appropriate conditions, the organic compound which contains a cation, will react by ion  
15 exchange with the clay which contains a negative layer lattice and exchangeable cations to form the organoclay products.

Other uses for such modified organoclays are those such as are disclosed in U. S. Patent 5,151,155, wherein organically modified smectite clays are utilized in a  
20 process for deinking wastepaper, and in U. S. Patent 4,677,158, wherein smectite-type clays which have been reacted with quaternary ammonium compounds are utilized as thickeners for aqueous suspensions, particularly latex paints and caulks. These modified organoclays differ from those of the present invention in the type of the agent with which they are intercalated. This modification produces organoclays  
25 with properties which make them suitable for use in the manufacture of thermoplastics.

OBJECTS OF THE INVENTION

30 It is an object of the present invention to prepare organoclay compositions having properties making them useful for the manufacture of thermoplastic compositions.

### SUMMARY OF THE INVENTION

In accordance with the present invention, it has unexpectedly been discovered that smectite-type clays, particularly montmorillonites, can be intercalated with particular agents which provide carbon-carbon double bonds, or serve as chain transfer agents, for free radical polymerization reactions. The thus produced organoclays can be utilized in the manufacture of thermoplastics, and particularly in the free radical polymerization of thermoplastics such as polystyrene and high impact polystyrene.

10

Thus, the present invention is concerned with an organoclay composition comprising the reaction product of a smectite-type clay having an ion exchange capacity of at least 50 meq. wt. per 100 g. clay (active basis), and mixture of a quaternary ammonium compound with either another quaternary ammonium compound containing a carbon-carbon double bond, or a chain transfer agent which is a thiol,  $\alpha$ -methylketone,  $\alpha$ -methylalcohol or a halogen compound.

15

### BRIEF DESCRIPTION OF THE DRAWING FIGURES

FIGURE 1 is a d-spacing tracing of a montmorillonite clay intercalated with 80 mer dimethyl-di-hydrogenated tallow ammonium chloride (2M2HT) and 10 mer DL-cysteine.

FIGURE 2 is a d-spacing tracing of a montmorillonite clay intercalated with 80 mer dimethyl-di-hydrogenated tallow ammonium chloride (2M2HT) and 20 mer DL-cysteine.

FIGURE 3 is a d-spacing tracing of a montmorillonite clay intercalated with 80 mer dimethyl-di-hydrogenated tallow ammonium chloride (2M2HT) and 10 mer N,N-dimethylaminomethacrylate "Q" salt methyl chloride.

30

FIGURE 4 is a d-spacing tracing of a montmorillonite clay intercalated with 80 mer dimethyl-di-hydrogenated tallow ammonium chloride (2M2HT) and 20 mer dimethylaminomethacrylate "Q" salt methyl chloride.


## 5 DESCRIPTION OF PREFERRED EMBODIMENTS

The smectite clays which are utilized as one of the starting materials of the present invention are those which have been conventionally utilized in the prior art.

Suitable smectite-type clays are those which have a cation exchange capacity of at  
 10 least 50 milliequivalents (meq.) weight (wt.) per 100 grams of clay (active basis). Useful clays for such purposes include the naturally occurring Wyoming variety of swelling bentonite and similar clays, and hectorite, which is a swelling magnesium-lithium silicate clay. The clays are preferably converted to the sodium form if they are not already in this form. This can be effected, again as is known in the art, by  
 15 a cation exchange reaction, or the clay can be converted via an aqueous reaction with a soluble sodium compound.

Smectite-type clays prepared synthetically can also be utilized, such as montmorillonite, bentonite, beidelite, hectorite, saponite, and stevensite. Such  
 20 clays, and processes for their preparation, are described in U. S. Patents 4,695,402, 3,855,147, 3,852,405, 3,844,979, 3,844,978, 3,671,190, 3,666,407, 3,586,478, and 3,252,757, all of which are herein incorporated by reference.

The quaternary ammonium compounds which can be utilized in the compositions of  
 25 the present invention are known agents typically utilized in the preparation of organoclays and include alkyl ammonium compounds of the formula:



- wherein  $R_1$ ,  $R_2$ ,  $R_3$  and  $R_4$  are independently selected from the group consisting of lineal or branched, saturated or unsaturated alkyl groups having 1 to 22 carbon atoms, aralkyl groups which are benzyl and substituted benzyl moieties, aryl group, beta, gamma-unsaturated groups having six or less carbon atoms, hydroxyalkyl groups having two to six carbon atoms, and hydrogen, with the proviso that at least one of the substituents is a lineal or branched saturated or unsaturated alkyl group; and X is the salt anion.
- 5
- 10 In formula I, the aralkyl groups include benzyl and substituted benzyl moieties including fused ring moieties, and have an alkyl portion consisting of lineal or branched chains of 1 to 22 carbon atoms. The aryl groups are those such as phenyl and substituted phenyl, including fused ring aromatic substituents.
- 15 The long chain alkyl groups may be derived from natural occurring oils including various vegetable oils, such as corn oil, coconut oil, soybean oil, cottonseed oil, castor oil and the like, as well as various animal oils or fats such as tallow oil. The alkyl radicals may likewise be petrochemically derived such as from alpha olefins.
- 20 Representative examples of useful branched, saturated groups include 12-methylstearyl and 12-ethylstearyl. Representative examples of useful branched, unsaturated radicals include 12-methyloleyl and 12-ethylloleyl. Representative examples of useful branched, saturated radicals include lauryl, stearyl, tridecyl, myristyl (tetradecyl), pentadecyl, hexadecyl, hydrogenated tallow, docosanyl.
- 25 Representative examples of unbranched, unsaturated and unsubstituted groups include oleyl, linoleyl, linolenyl, soya and tallow.

- Examples of aralkyl include benzyl and substituted benzyl moieties such as those derived from benzyl halides, benzhydryl halides, trityl halides,  $\alpha$ -halo- $\alpha$ -phenylalkanes wherein the alkyl chain has from 1 to 22 carbon atoms, such as 1-halophenylethane, 1-halo-1-phenyl propane and 1-halo-1-phenyloctadecane.
- 30

Substituted benzyl moieties, such as would be derived from ortho-, meta- and para-chlorobenzyl halides, para-methoxybenzyl halides, ortho-, meta and para-nitrobenzyl halides, and ortho-, meta and para-alkylbenzyl halides wherein the alkyl chain contains from 1 to 22 carbon atoms; and fused ring benzyl-type

5 moieties, such as would be derived from 2-halomethylnaphthalene, 9-halomethylantracene and 9-halomehtylphenanthrene, wherein the halo group would be defined as chloro, bromo, iodo, or any other such group which serves as a leaving group in the nucleophilic attack of the benzyl type moiety such that the nucleophile replaces the leaving group on the benzyl type moiety.

10

Examples of aryl groups would include phenyl such as in N-alkyl and N, N-Ndialkyl anilines, wherein the alkyl groups contain between 1 to 22 carbon atoms; ortho-, meta and pre-nitrophenyl, ortho-, meta- and para-alkyl phenyl, wherein the alkyl group contains between 1 and 22 carbon atoms, 2-, 3-, and 4-halophenyl

15 wherein the halo group is defined ass chloro, bromo, or iodo, and 2-, 3-, and 4-carboxyphenyl and esters thereof, where the alcohol of the ester is derived from an alkyl such as carbon atoms, aryl such as phenol, or aralkyl such as benzyl alcohols; fused ring aryl moieties such as naph-thalene, anthracene, and phenanthrene.

20 The  $\beta, \gamma$ -unsaturated alkyl group may be selected from a wide range of materials. These compounds may be cyclic or acyclic, unsubstituted or substitute with aliphatic radicals containing up to 3 carbon atoms such that the total number of aliphatic carbons in the  $\beta, \gamma$ -unsaturated radical is 6 or less. The  $\beta, \gamma$ -unsaturated alkyl radical may be substituted with an aromatic ring that likewise is conjugated

25 with he unsaturation of the  $\beta, \gamma$ -moiety or the  $\beta, \gamma$ -radical is substituted with both aliphatic radicals and aromatic rings.

Representative examples of cyclic  $\beta, \gamma$ -unsaturated alkyl groups include 2-cyclohexenyl and 2-cyclopentenyl. Representative examples of acyclic  $\beta, \gamma$ -

30 unsaturated alkyl groups containing 6 or less carbon atoms include propargyl; allyl(2-propeny); croty(2-butenyl); 2-pentenyl; 2-hexenyl; 3-methyl-2-butenyl; 3-

- methyl-2-pentenyl; 2,3-dimethyl-2-butenyl; 1,1-dimethyl-2-propenyl; 1,2-dimethyl propenyl; 2,4-pentadienyl; and 2,4-hexadienyl. Representative examples of acyclic-aromatic substituted compounds include cinnamyl (3-phenyl-2-propenyl); 2-phenyl-2-propenyl; and 3-(4-methoxyphenyl)-2-propenyl. Representative examples of
- 5 aromatic and aliphatic substituted materials include 3-phenyl-2-cyclohexenyl; 3-phenyl-2-cyclopentenyl; 1, 1-dimethyl-3-phenyl-2-propenyl; 1,1,2-trimethyl-3-phenyl-2-propenyl; 2,3-dimethyl-3-phenyl-2-propenyl; 3,3-dimethyl-2-phenyl-2-propenyl; and 3-phenyl-2-butenyl.
- 10 The hydroxyalkyl group is selected from a hydroxyl substituted aliphatic radical wherein the hydroxyl is not substituted at the carbon adjacent to the positively charged atom, and the group has from 2 to 6 aliphatic carbons. Representative examples include 2-hydroxy-ethyl (ethanol); 3-hydroxypropyl; 4-hydroxypentyl; 6-hydroxyhexyl; 2-hydroxypropyl (isopropanol); 2-hydroxybutyl; 2-hydroxypentyl; 2-
- 15 hydroxyhexyl; 2-hydroxycyclohexyl; 3-hydroxycyclohexyl; 4-hydroxypentyl; 2-hydroxycyclopentyl; 3-hydroxycyclo-pentyl; 2-methyl-2-hydroxypropyl; 1,1,2-trimethyl-2-hydroxypropyl; 2-phenyl-2-hydroxyethyl; 3-methyl-2-hydroxybutyl; and 5-hydroxy-2-pentenyl.
- 20 A preferred compound of Formula I contains at least one linear or branched, saturated or unsaturated alkyl group having 12 to 22 carbon atoms and at least one linear or branched, saturated or unsaturated alkyl group having 1 to 12 atoms. The preferred compound of Formula I may also contain at least one aralkyl group having a linear or branched, saturated or unsaturated alkyl group having 1 to 12
- 25 carbons in the alkyl portion. Mixtures of these compounds may also be used.

Especially preferred compound of Formula I is a compound where  $R_1$  and  $R_2$  are hydrogenated tallow.  $R_3$  and  $R_4$  are methyl or where  $R_1$  is hydrogenated tallow,  $R_2$  is benzyl and  $R_3$  and  $R_4$  are methyl or a mixture thereof such as 90% (equivalents)

30 of the former and 10% (equivalents) of the latter.



The salt anion of the ammonium salt may be methosulfate, ethosulfate, methylcarbonate, ethylcarbonate, chloride, bromide, or mixtures thereof, and is most preferably a methosulfate ion. The salt anion may also, however, be nitrate, hydroxide, acetate, or mixtures of these.

5

Illustrative of the numerous patents which describe organic cationic salts, their manner of preparation and their use in the preparation of organophilic clays are commonly assigned U.S. Pat. Nos. 2,966,506, 4,081,496, 4,105,578, 4,116,866, 4,208,218, 4,391,637, 4,410,364, 4,412,018, 4,434,075, 4,434,076, 4,450,095 and 4,517,112, the contents of which are incorporated by reference.

10

The quaternary ammonium compound which contains a carbon-carbon double bond for the free radical polymerization can be any of the above-described compounds of formula I which contain the necessary double bond. In a preferred embodiment, the organoclay of the present invention thus contains two different types of quaternary ammonium compounds. Alternatively, a chain transfer agents can be included in place of the second quaternary compound. These include thiols, for example DL-cysteine,  $\alpha$ -methylketones, such as acetone,  $\alpha$ -methylalcohols, such as isopropanol, or halogen compounds, such as chloroform and carbontetrachloride. Particularly useful, due to its efficiency in chain transfer processes, is DL-cysteine.

15

20

The chain transfer agent present in combination with the quaternary ammonium salt in the organoclays of the present invention determine the particularly advantageous properties of the resultant organoclays of the present invention. Thus, the incorporation of the chain transfer agents with the quaternary ammonium compound provide modified organoclays which can be directly utilized in the process for the preparation of thermoplastics, and particularly polystyrene and high impact polystyrene materials.

25

Highly preferred embodiments of the present invention are organoclays which comprise the reaction product of smectite-type clays with a mixture of a quaternary

30

ammonium compound such as dimethyl-di-hydrogenated tallow ammonium chloride and DL-cysteine.

The quaternary ammonium compounds useful in the present invention of the present invention can be prepared by various methods known by those of ordinary skill in the art. In a preferred method, the quaternary ammonium compound is prepared by the reaction of a tertiary amine and an alkylating agent. Some alkylating agents, well known to those practicing the art, include organic halides such as methyl chloride, diorganosulfates such as dimethyl sulfate, or diorgano carbonates, such as dimethyl carbonate. This method of preparation is described in *ENCYCLOPEDIA OF CHEMICAL TECHNOLOGY* edited by Kirk/Othmer (Third Edition, Vol 19, page 521-531) which is incorporated herein by reference. Many of the quaternary ammonium compounds, such as dimethyl-di-hydrogenated tallow ammonium chloride, are also commercially available in industrial quantities.

15

The amount of the quaternary ammonium compound reacted with the smectite-type clay depends upon the specific clay and the desired end use. Typically, the amount of cation ranges from about 0.1 to about 150%, preferably from about 100 to about 130% of the cation exchange capacity of the clay. Thus, for example, when bentonite is used, the amount of cation reacted with the clay will range from about 85 to about 143 milliequivalents, preferably from about 95 to about 124 milliequivalents per 100 grams of clay, 100% active basis.

20

The amount of the chain transfer agent reacted with the smectite-type clay depends upon the specific clay and the desired end use. Typically, the amount of cation ranges from about 0.1 to about 150%, preferably from about 100 to about 130% of the cation exchange capacity of the clay. Thus, for example, when bentonite is used, the amount of cation reacted with the clay will range from about 85 to about 143 milliequivalents, preferably from about 95 to about 124 milliequivalents per 100 grams of clay, 100% active basis.

25

30

A further embodiment of the present invention is the process for preparing the organoclay composition comprising the reaction product of a smectite-type clay having an ion exchange capacity of at least 50 meq. wt. per 100g. clay (active basis), and a mixture of a quaternary ammonium compound and a chain transfer agent which comprises:

- a) dispersing a smectite type clay having an ion exchange capacity of at least 50 meq. wt. per 100 g. clay in an aqueous media;
  - b) heating the dispersing of step (a) to a temperature in excess of 30° C;
  - c) adding the heated dispersion of step (b) of the quaternary ammonium salt, in the desired milliequivalent ratio;
  - d) adding the mixture of step (c) to a solution of the chain transfer agent, pretreated with a strong mineral acid, if necessary; and
  - e) agitating the mixture of step (d) to effect completion of the reaction.
- The organoclay composition of the present invention is thus prepared by admixing an aqueous dispersion of the smectite-type clay, warmed to a temperature in excess of 30°C., with a quaternary ammonium compound and the chain transfer agent to exchange the metal counterions that are naturally present in the smectite-type clay. The reaction is typically conducted at a temperature within the range of from about 40°C. to about 100 °C. for a period of time sufficient for the quaternary ammonium compound and the chain transfer agent to react with the clay particles.

Preferably, the clay is dispersed in the water at a concentration from about 3% to about 15% by weight and the slurry is centrifuged to remove non-clay impurities.

The slurry is then agitated and heated to the desired temperature, and the quaternary ammonium salt added in the desired milliequivalent ratio. To this mixture is then added the chain transfer agent which has, if necessary, been pretreated, typically by

the addition of a strong mineral acid such as hydrochloric acid, to result in the protonated form, in the desired milliequivalent ratio. The quaternary ammonium compounds are typically liquids, but they can be dispersed in water to facilitate the reaction. Agitation is continued to effect completion of the reaction.

5

The amount of the quaternary ammonium compound and the chain transfer agent added to the smectite-type clay for the purposes of this invention must be sufficient to impart to the clay the enhanced characteristics desired. The milliequivalent ratio is defined as the number of milliequivalents of the alkoxylated quaternary ammonium compound, per 100 grams of clay, 100% active basis. The typical smectite-type clays of this invention have a milliequivalent ratio of from about 10 to about 150. The preferred milliequivalent ratio will vary depending on the characteristics of the particular quaternary ammonium compound and the chain transfer agent utilized and the end use for the resultant product.

15

The organoclay composition of the present invention is utilized as an additive to polymer composites and molding compositions, and especially to enhance the properties of same. The polymer composites possess improved physical properties i.e, heat and chemical resistance and barrier properties and have utility as automotive parts, aircraft parts, building materials, durables, coatings, films, food packaging and computer housings.

These polymer composites exhibit reduced thermal expansion, improved dimensional stability, enhanced barrier properties, enhanced modulus, even when exposed to polar media such as water or methanol, improved ignition resistance and nondrip characteristics, and enhanced heat resistance as compared to the compositions which do not include the interrelated inorganic substrate.

These polymer composites can also be molded into articles of manufacture by conventional shaping processes, such as melt spinning, casting, vacuum molding, injection molding and extruding. Examples of such molded articles are components for technical equipment, durables, apparatus castings, household equipment, sports

equipment, bottles, containers, components for the electrical and electronics industries, car components, circuits, fibers, semi-finished products which can be shaped by machining and the like. The use of the materials for coating articles by means of powder coating processes is also possible, as is their use as hot-melt  
5 adhesives.

These molding compositions can also be used in the production of sheets and panels having valuable properties. Such sheets and panels may be shaped by conventional processes such as vacuum processing or by hot pressing to form useful objects.

10 The sheets and panels are also suitable as coating materials for other materials comprising, for example, wood, glass, ceramic, metal or other plastics, and outstanding strengths can be achieved using conventional adhesion promoters, for example, those based on vinyl resins. The sheets and panels can also be laminated with other plastic films and this is preferably effected by coextrusion, the sheets  
15 being bonded in the molten state. The surfaces of the sheets and panels, including those in the embossed form, can be improved or finished by conventional methods, for example by lacquering or by application of protective films.

These polymer composites are also useful for fabrication of extruded films and film  
20 laminates, as for example, films for use in food packaging. Such films can be fabricated using conventional film extrusion technique.

The invention will now be illustrated by a series of Examples, which are intended to set forth typical and preferred procedures to be utilized in the practice of the  
25 invention.

### EXAMPLE 1

The preparation of a smectite-type clay composition comprising the reaction product  
30 of a smectite-type clay and a quaternary ammonium compound (80 mer) and a chain transfer agent (10 mer) is prepared as follows:

5000 grams of water is heated to 140°F, and to this is added 2M2HT quat (dimethyl-di-hydrogenated tallow ammonium chloride) at a level of 80 mer. A solution of 12 N HCl is added to this solution to act as the protonating agent for the DL-cysteine. The DL-cysteine, at a level of 10 mer, is then added to the solution of the quat/HCl/H<sub>2</sub>O, and mixed for a period of about 15 minutes. A slurry of an aqueous three pass slurry of montmorillonite containing 3.39 % solids in a 5 gallon tank is heated to a temperature of about 140° F., and 12 N HCl is added to adjust the pH from 8.8 to 6.8. This slurry is then added to the quat/DL-cysteine solution, and reacted for a period of about 45 minutes. The reaction mixture is then filtered, with pressure on the filter cake, re-slurried, and mixed for an additional period of about 10 minutes. Then, the mixture is again filtered, fluid bed dried at a temperature of about 80°C., and milled on a .2 mm screen to afford a montmorillonite clay intercalated with 80 mer dimethyl-di-hydrogenated tallow ammonium chloride and 10 mer DL-cysteine, with a d-spacing tracing as shown in Figure 1.

### EXAMPLE 2

The preparation of a smectite-type clay composition comprising the reaction product of a smectite-type clay and a quaternary ammonium compound (80 mer) and a chain transfer agent (20 mer) is prepared as follows:

5000 grams of water is heated to 140°F, and to this is added 2M2HT quat (dimethyl-di-hydrogenated tallow ammonium chloride) at a level of 80 mer. A solution of 12 N HCl is added to this solution to act as the protonating agent for the DL-cysteine. The DL-cysteine, at a level of 20 mer, is then added to the solution of the quat/HCl/H<sub>2</sub>O, and mixed for a period of about 15 minutes. A slurry of an aqueous three pass slurry of montmorillonite containing 3.39 % solids in a 5 gallon tank is heated to a temperature of about 140° F., and 12 N HCl is added to adjust the pH from 8.8 to 6.8. This slurry is then added to the quat/DL-cysteine solution, and reacted for a period of about 45 minutes. The reaction mixture is then filtered, with pressure on the filter cake, re-slurried, and mixed for an additional period of

about 10 minutes. Then, the mixture is again filtered, fluid bed dried at a temperature of about 80°C., and milled on a .2 mm screen to afford a montmorillonite clay intercalated with 80 mer dimethyl-di-hydrogenated tallow ammonium chloride and 20 mer DL-cysteine, with a d-spacing tracing as shown in

5 Figure 2.

### EXAMPLE 3

Repetition of the procedure detailed in Example 1, using 80 mer dimethyl-di-  
10 hydrogenated tallow ammonium chloride and 10 mer N,N-  
dimethylaminoethylmethacrylate "Q" salt methyl chloride afforded a  
montmorillonite clay intercalated with 80 mer dimethyl-di-hydrogenated tallow  
ammonium chloride and 10 mer N,N-dimethylaminoethylmethacrylate "Q" salt  
methyl chloride, with a d-spacing tracing as shown in Figure 3.

15

### EXAMPLE 4


Repetition of the procedure detailed in Example 1, using 80 mer dimethyl-di-  
hydrogenated tallow ammonium chloride and 20 mer N,N-  
20 dimethylaminoethylmethacrylate "Q" salt methyl chloride afforded a  
montmorillonite clay intercalated with 80 mer dimethyl-di-hydrogenated tallow  
ammonium chloride and 20 mer N,N-dimethylaminoethylmethacrylate "Q" salt  
methyl chloride, with a d-spacing tracing as shown in Figure 4.

25

WHAT IS CLAIMED IS:

1           1. An organoclay composition comprising the reaction product of a smectite-  
2 type clay having an ion exchange capacity of at least 50 meq. wt. per 100 g. clay  
3 (active basis), and mixture of a quaternary ammonium compound with either  
4 another quaternary ammonium compound containing a carbon-carbon double bond,  
5 or a chain transfer agent which is a thiol,  $\alpha$ -methylketone,  $\alpha$ -methylalcohol or a  
6 halogen compound.

1           2. The composition according to Claim 1 wherein the quaternary  
2 ammonium compound is of the formula:



10 wherein  $R_1$ ,  $R_2$ ,  $R_3$  and  $R_4$  are independently selected from the group consisting of  
11 linear or branched, saturated or unsaturated alkyl groups having 1 to 22 carbon  
12 atoms, aralkyl groups which are benzyl and substituted benzyl moieties, aryl group,  
13 beta, gamma-unsaturated groups having six or less carbon atoms, hydroxyalkyl  
14 groups having two to six carbon atoms, and hydrogen, with the proviso that at least  
15 one of the substituents is a linear or branched saturated or unsaturated alkyl group;  
16 and X is the salt anion.

1           3. The composition according to Claim 2 wherein the chain transfer agent is  
2 a thiol.




1           4. The composition according to Claim 2 wherein the quaternary  
2 ammonium compound is dimethyl-di-hydrogenated tallow ammonium chloride and  
3 the chain transfer agent is DL-cysteine.

1           5. A process for the preparation of an organoclay composition comprising  
2 the reaction product of a smectite-type clay having an ion exchange capacity of at  
3 least 50 meq. wt. per 100 g. clay (active basis), and mixture of a quaternary  
4 ammonium compound with either another quaternary ammonium compound  
5 containing a carbon-carbon double bond, or a chain transfer agent which is a thiol,  
6  $\alpha$ -methylketone,  $\alpha$ -methylalcohol or a halogen compound, which comprises:

- 7
- 8           a) dispersing a smectite-type clay having an ion exchange capacity of at least  
9 50 meq. wt. per 100 g. clay, in an aqueous media;
- 10
- 11           b) heating the dispersion of step (a) to a temperature in excess of 30° C;
- 12
- 13           c) adding to the heated dispersion of step (b) of a quaternary ammonium salt,  
14 in the desired milliequivalent ratio;
- 15
- 16           d) adding the mixture of step (c) to a solution of the chain transfer agent,  
17 pretreated with a strong mineral acid, if necessary; and
- 18
- 19           e) agitating the mixture of step (d) to effect completion of the reaction.

1           6. The process according to Claim 5 wherein the quaternary ammonium  
2 compound of formula I has the formula



9


10 wherein  $R_1$ ,  $R_2$ ,  $R_3$  and  $R_4$  are independently selected from the group consisting of  
11 linear or branched, saturated or unsaturated alkyl groups having 1 to 22 carbon  
12 atoms, aralkyl groups which are benzyl and substituted benzyl moieties, aryl group,  
13 beta, gamma-unsaturated groups having six or less carbon atoms, hydroxyalkyl  
14 groups having two to six carbon atoms, and hydrogen, with the proviso that at least  
15 one of the substituents is a linear or branched saturated or unsaturated alkyl group;  
16 and X is the salt anion.

1 7. The process according to Claim 5 wherein the chain transfer agent is a  
2 thiol.

1 8. The process according to Claim 5 wherein the quaternary ammonium  
2 compound is dimethyl-di-hydrogenated tallow ammonium chloride and the chain  
3 transfer agent is DL-cysteine.

1 / 4


FIG. 1



SUBSTITUTE SHEET (RULE 26)

2 / 4


FIG.2



SUBSTITUTE SHEET (RULE 26)


3 / 4

FIG. 3



SUBSTITUTE SHEET (RULE 26)

FIG. 4



SUBSTITUTE SHEET (RULE 26)

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/US97/02706

**A. CLASSIFICATION OF SUBJECT MATTER**

IPC(6) : C04B 14/00, 14/10, 33/02; C09C 1/42

US CL : 106/486, 487, 287.17; 501/148; 252/315.2

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 106/486, 487, 287.17; 501/148; 252/315.2

IPC(6): C04B 14/00, 14/10, 33/02

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched  
noneElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
none**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4,425,244 A (HOUSE) 10 JANUARY 1984, SEE COLUMN 3, LINE 53-COLUMN 9, LINE 61.	1,2
Y	US 5,429,999 A (NAE ET AL.) 04 JULY 1995, SEE THE CLAIMS.	1-6
Y	US 4,743,305 A (DOIDGE ET AL.) 10 MAY 1988, SEE COLUMN 1, LINE 2-COLUMN 2, LINE 36 AND THE EXAMPLES.	1,2,5,6

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	* T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
* A		document defining the general state of the art which is not considered to be of particular relevance
* B		earlier document published on or after the international filing date
* L		document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
* O		document referring to an oral disclosure, use, exhibition or other means
* P		document published prior to the international filing date but later than the priority date claimed
	* X	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
	* Y	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
	* A	document member of the same patent family

Date of the actual completion of the international search 09 APRIL 1997	Date of mailing of the international search report 11 JUL 1997
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230	Authorized officer <i>Michael Marcheschi</i> MICHAEL MARCHESCHI Telephone No. (703) 308-0661

Form PCT/ISA/210 (second sheet)(July 1992)\*

THIS PAGE BLANK (USFTO)